OLED Digital Durometer

The OLED display is visible in dark environments Standard and long probe models are available

- OLED display is visible in dark environments
- Push-button operation and simple menus control programming functions
- Modes: Peak, Single/ Dual Timer Hold and Real Time
- Auto Average— average a user-selectable number of readings.
- Selectable resolution: 1 and 0.1
- Accuracy: ±1 (±2 Type 00)
- 400 data memory or USB output
- True compliance to ASTM D2240. Calibration cert traceable to NIST included; optional ISO-17025 certificate available
- Rugged metal construction, powered by the rechargeable battery or AC adapter
- Manual test stands and motorized test stands are available.

Digital durometers have three modes; Peak records the highest reading, Timer Hold records the decrease in the reading a specified time after the peak is reached and Real Time. Auto Average averages a selectable number of peak readings. Hardness data can be transmitted via USB to PCs or saved in the 400 data memory. Optional data acquisition software is available.

The durometers feature push-button operation in a lightweight, durable, metal housing. Standard probe and long probe mod-

Mo	dels				
Standard	Long Probe	Scale	Scale Standard		
TKD-A*	TKD-AL	Shore A	ASTM D2240, ISO 868, 7619		
TKD-B	TKD-BL	Shore B	ASTM D2240		
TKD-C	TKD-CL	Shore C	ASTM D2240		
TKD-AC	TKD-ACL	Asker C	JIS K7312		
TKD-D*	TKD-DL	Shore D	ASTM D2240, ISO 868, 7619		
TKD-D0	TKD-DOL	Shore DO	ASTM D2240		
TKD-E	TKD-EL	Shore E	ASTM D2240		
TKD-0	TKD-OL	Shore 0	ASTM D2240		
TKD-00	TKD-00L	Shore 00	ASTM D2240		

*Most popular models

els are available. Operates on an internal rechargeable battery or AC adapter.

Comparison of Hardness Scales

This chart is an approximate comparison of scales. It is not a conversion chart. When selecting a scale for your material aim for measurements of 50. Measurements below 10 and above 90 are not recommended.

Also consider the indentor shape and its effect on the material: cone, truncated cone or hemispherical.

Scale	Indentor Shape*	Extra Soft		Soft	Medium	Hard
00	U	30	50	90		
Asker C	U	30	50	90		
E	U	10	50	90		
0	U			50	90	
Α			30	50	90	
В	∇		10	50		90
DO				0	50	90
С	∇			10	50	90
D	∇			30	50	90
		Sponge & Foam Rubber		Soft Rubber	Normal Rubber	Hard Rubber & Plastics






C€ F© IC

Long probe model

Optional OR-1 Ring Add a wrist strap to the ring and reduce drop damage (strap not included).

Optional Data Acquisition Software SW-1-TK captures and analyzes peak and timer data from TK digital durometers.



Wireless Output Durometers are available. Please Inquire.



Specifications subject to change without notice.

